



**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
Tel. 059 822417 r.a. - Fax 059380281 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) - [www.modenacentroprove.com](http://www.modenacentroprove.com)  
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

MECCANICA

ECOLOGIA

CERAMICA

ALIMENTARE

Modena, 08/08/19

To **GRUPPO ROMANI S.P.A.**  
VIA A.VOLTA 9  
23/25  
42013 CASALGRANDE RE

Attn. **sig. Marastoni**

MATERIAL and/or SAMPLE to be tested	Denomination of the Sample	Client Reference – Your delivery	date
PORCELAIN TILES	1066578 FOSSIL BRUNO RET 60X60	NS RITIRO	15/7/19

Here attached, you will receive the Test Report of Serial No. **20195778/n**, which shows the results of tests required.

**MODENA CENTRO PROVE**

MODENA CENTRO PROVE  
  
Director  
Sant'Unione dr. Giuseppe



MODENA CENTRO PROVE s.r.l.

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
Tel. 059 822417 r.a. - Fax 059380281 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) -  
[www.modenacentroprove.com](http://www.modenacentroprove.com)  
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 C.F. e P. IVA n. 01592020364



LAB N°1018L

Membro degli Accordi di Mutuo Riconoscimento EA, IAF e ILAC


Signatory of EA, IAF and ILAC Mutual Recognition Agreements


## TEST REPORT: 20195778/1

Modena, 08/08/19

<b>CUSTOMER</b>	<b>GRUPPO ROMANI S.P.A. - - VIA A.VOLTA 9 23/25 - 42013 - CASALGRANDE - RE</b>
<b>MATERIAL and/o SAMPLE to be tested</b>	PORCELAIN TILES;
<b>Denomination</b>	1066578 FOSSIL BRUNO RET 60X60;
<b>Date of sample reception</b>	15/07/2019;
<b>Date of sample acceptance</b>	15/07/2019;
<b>Kind of test executed</b>	Determination of the Resistance to Abrasion
<b>Referring standards</b>	UNI EN ISO 10545-7:2000
<b>Shifting from standards</b>	No one
<b>Equipment</b>	Abrasion tester cod. MCP C127
<b>Subcontracted phases</b>	No one
<b>Sampling made by</b>	Customer

*The test results showing in this Report are only referred to the sample taken by our staff or supplied by the Customer. He commits himself to reproduce integrally this document. Partial reproduction is forbidden.  
The times of retain of the samples was indicated in the offer related to the test report.*

Examiner  
  
p.i. Nassetti Luca

MODENA CENTRO PROVE  
  
Ceramic Dept. Responsible  
P.I. De Pasquale Roberto

MODENA CENTRO PROVE  
  
Director  
Sant'Unione dr. Giuseppe



**MODENA CENTRO PROVE s.r.l.**  
 Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
 Tel. 059 822417 r.a. - Fax 059380281 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) -  
[www.modenacentroprove.com](http://www.modenacentroprove.com)  
 C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 C.F. e P. IVA n. 01592020364



LAB N°1018L  
 Membro degli Accordi di Mutuo Riconoscimento EA, IAF e ILAC  
 Signatory of EA, IAF and ILAC Mutual Recognition Agreements

## DETERMINATION OF THE RESISTANCE TO ABRASION

Beginning date : 06/08/19

Analysis ending date : 06/08/19

**SAMPLE** : Ceramic tiles, marked «**1066578 FOSSIL BRUNO RET 60X60** »

The test was performed by rotating an abrasive load on the glazed surface of the tile; at the end of the test, the test specimens subjected to abrasion were compared with control tiles under a light source of 300 Lux, at the distance of 2 m and at the height of 1.65 m.

### RESULTS

Stage of abrasion with visible variation (n° revolutions): 750  
 Abrasion class: 3

### CLASSIFICATION




#### 1. Classification PEI

Abrasion Stage: abrasion visible at n° of turn	Class
100	0
150	1
600	2
750 - 1500	3
2100 – 6000 – 12000	4
>12000 and is in accordance with the stain resistance test UNI EN ISO 10545-14	5

### REQUIREMENTS

(Standard UNI EN 14411:2016 Annex G)

Report abrasion class and cycles passed.

<p>Examiner            p.i. Nassetti Luca</p>	<p>MODENA CENTRO PROVE            Ceramic Dept. Responsible          P.I. De Pasquale Roberto</p>	<p>MODENA CENTRO PROVE            Director          Sant'Unione dr. Giuseppe</p>
--	--	---