

**TEST REPORT**

OUR REF. 599/04

DATE 16/11/2004

Spett.le

CERAMICA

SERENISSIMA C.I.R. S.p.A.

Stabilimento ROTEGLIA RE

Via Provinciale per Baiso, 13

42010 ROTEGLIA RE

NORM DIN 51130**Determination of anti-slippery characteristic**

Work's zone with high risk of slippery

Procedure of test walking – inclined platform.

The test regard work's zone with high risk of slippery; the procedure it previews a slanted plan that it comes covered from the subject participants to the test, whose surface is paved with the material in object, preventively greased with having oil 10 viscosity SAE W 30. During the execution one determines if the material in examination can be suitable for puts down it in specific atmospheres of job. The medium degree of inclination correspondent to the feeling of insecurity of the operator who walks on the plan, defines the classification of the material in one of the five groups that serve like parameter in order to establish the effectiveness degree anti-slippery.

Samples arrived at 10/11/2004 (sampling executed by Commitment)

DESCRIPTION TILES : 31,7x31,7 cm
SERIES : "QUINTANA"
TYPE : "SPADA A 55"

Slide angle : 11,7°**Classification :** R10**LEGEND:****Total of the medium values**

from 6° to 10°
 over 10° until 19°
 over 19° until 27°
 over 27° until 35°
 over 35°

Group classification

R 9
 R 10
 R 11
 R 12
 R 13

GEOCERAMIC RESEARCHES
 LABORATORIO TECNOLOGICO
 40050 MONTE SAN PIETRO (BO) - ITALY

